

ULTRAFINO

SKIMCOAT

DESCRIPTION

ULTRAFINO Skimcoat cement-based powder for thin plastering applications. When mixed with water, the smooth creamy consistency makes it easy to correct surface imperfections prior to painting.

FEATURES & BENEFITS

- Excellent workability
- Good adhesion to concrete surfaces
- No cracking or flaking
- Minimal powdering of surface when sanded
- No primer needed (for White finish)

RECOMMENDED USES

- For EXTERIOR and INTERIOR plastered concrete applications. (Surface of walls, ceilings, beams and columns)
- For pre-cast and poured concrete

COVERAGE

One (1) bag of 20 kg product can cover up to 20 m² at 1 mm thickness

VARIANTS

COLOR	PACK SIZE
White	Available in 20 kg and 2 kg
Grey	Available in 20 kg

SHELF LIFE

Twelve (12) months from date of manufacture when stored off the ground in a cool, dry weather-proof environment

DIRECTIONS FOR USE

SURFACE PREPARATION

1. Surface must be structurally sound, clean, and free from dust, oil, paint, grease and other contaminants.
2. For holes that are more than 2 mm deep, pre-patching and filling is required, or build-up application may be employed.

MIXING

Manual mixing

1. In a clean container, gradually add 7 liters of water to 20 kg ULTRAFINO Skimcoat.
2. Adjust the water depending on the desired consistency.
3. Mix thoroughly using a shovel until the mixture becomes homogenous, and free from lumps.
4. Let the mixture stand for 2 -3 minutes.



Mechanical mixing

1. In a clean container, with approximately 7 liters of water, gradually pour 20 kg of ULTRAFINO Skimcoat.
2. Continuously mix using an electric paddle mixer.
3. Mix thoroughly until the mixture becomes homogenous, and free from lumps and air packets.
4. Let the mixture stand for 2-3 minutes.

APPLICATION

1. Damp the substrate with water.
2. Apply the mixture using a flat-edge trowel. The applied area may be sanded to attain a flat and a more even surface.
3. Use a wet sponge to wash the surface, and then let dry for topcoat finishes.
4. Additional coatings on some surfaces might be needed as per requirement for better results.
5. To increase thickness, a second or third coat may be applied, for as long as the total thickness is within the recommended thickness.
6. An interval of 30 - 60 minutes in between coats is recommended, depending on site conditions.
7. When sanding, use sandpaper 120 or above.

PHYSICAL PROPERTIES

Color	White or Grey
Setting Time	30 min. to 1 hr. (depending on weather conditions)
Pot Life	Up to 2 hr.
Curing Time	12 to 48 hr.
Thickness	Featheredge 0 - 2mm

DISCLAIMER:

The information in this Technical Data Sheet is intended for the assistance of users and is of a general nature. It reflects the extent of our knowledge and experience of our products and is based on tests which we believe to be reliable. However, no guarantee of accuracy can be given due to the wide range of surfaces, environmental and field conditions and variations encountered in raw materials, manufacturing equipment and methods at the place where the work is performed. Some of these will be beyond our knowledge and control. Users are asked to make sure that the TDS in their possession is the latest issue. Likewise, we recommend users carry out their own tests to determine the suitability of the product for their particular purposes. Any claim for a defective product must be filed within 30 days of discovery of a problem and must be submitted with written proof of purchase. Claims are not transferrable or assignable and extend only to the original purchaser/user. Bostik reserves the right to inspect and alleged failure and no responsibility will be accepted unless Bostik is given the opportunity to do so. Bostik limits its liability to the replacement of the product/s proven faulty.

BOSTIK PHILIPPINES, INC.
35/F Penthouse Raffles Corporate Center
F. Ortigas Jr. Road, Ortigas Business Center, Pasig City Philippines
+63 2 7900 5856
www.bostik.com/Philippines

BOSTIK HOTLINE

Smart help +63 2 7900 5656